

# Wax Comparison Sheet

\*Top Seller in Brand

Recommended for:

	Make-up	Melt Point	Adhesion	Form	Pour Temp	F/ L	Tarts	Massage
<b>Golden Brands</b>								
GB-415 Container Wax	100% Soy	120°-125°		Flake	90°-100°	8%-10%		
GB-444 Container Wax	Soy & Soy based additives	120°-125°		Flake	125°-145°	9%-11%		
GB-464 Container Wax *	Soy & Soy based additives	115°-120°	Adhesion	Flake	125°-145°	7%-9%		
GB- Wax Tart & Melt Wax	Soy & Bio based additives	120°-125°	Great Mold Release	Flake	Heat to 170° Pour above 150°	5%-10%	X	
<b>NatureWax</b>								
NW-C1 Container Wax	100% Soy/Palm	124°-130°	Complete Pull-Away	Flake	110°-135°	Up to 8%	X	X
NW-C3 Container Wax *	100% Soy	124°-130°	Complete Adhesion	Flake	120°-165°	Up to 8%	X	X
NW-Elite 200 Container Wax	100% Soy	125°-135°	Complete Pull-Away	Slab	140°-185°	Up to 12%	X	
NW-S113 (Base/Blending) Container Wax	100% Soy	115°	Adhesion	Flake	105°-120°	Up to 10%	X	
<b>EcoSoya</b>								
ES-CB 135 Container Wax	100% Vegetable	122°	Adhesion	Flake	140°	12%		
ES-CB Advanced Container Wax *	100% Vegetable	111°	Contracts Consistently	Flake	140°	12%		
ES-CB Xcel Container Wax	100% Soy	125°	Adhesion	Flake	140°	12%		
ES-PB Pillar Wax	100% Vegetable	130°	Self-releasing	Flake	155°	12%	X	